

## Product Description

Designed as a root penetration barrier which protects the roofing membrane against potential ingress from perennial and grass root systems. XF112 is a flexible and impermeable sheet made of low density polyethylene (LDPE) that is chemically inert as well as physically and chemically compatible with all roofing and waterproofing membranes. It is also resistant to fats, oils, chemicals, microorganisms, and UV. XF112 is accordion folded and tightly rolled onto a heavy-duty core for ease of handling and time saving installation.



## Technical Data

### Mechanical Properties

Material	LDPE
Thickness (mm)	0.5
Weight (kg/m <sup>2</sup> )	0.46
Tensile strength (N/cm)	119-168
Elongation at film break (%)	700-900
Tear resistance (N/mm)	44-53
Puncture resistance (N)	107-178
Volatile loss (%)	<1
Dimensional stability (%)	<2
Use temperature (°C)	-56/82
2% secant modulus (max) MPa	414-207
Carbon black content TGA (%)	1.6-2.4

### Packaging Properties

Color	Black
Width (m)	3.86
Length (m)	33.52
Area (m <sup>2</sup> )	129.4
Diameter of roll (cm)	38
Length of roll (m)	2.06

## Recommended application

- Unroll XF112 Root barrier roll, cut to required length.
- Product comes folded in half lengthwise. Open the fold to expose true width of product.
- Install loose-laid with a min. 300mm overlap onto adjacent root barrier material.
- Continue root barrier under the non-vegetated zones and up the sides of the roof edges (wall/parapet) to the top of vegetated system.
- Start next row with a partial roll so the end joints stagger between rows.
- Cut and fit tightly along roof edge and around penetrations
- Cover immediately to avoid displacement by wind.